



.015 mil Matte White Styrene

MGX-1733

12" x 18"

1500 FENPARK DRIVE, FENTON, MO 63026 P: 636.349.6401 F: 636.349.6402 MGXDIGITAL.COM SALES@MGXDIGITAL.COM

- Typical uses include packaging and one-time use items, printed toys & games, POP displays, silk screen printing
- Excellent printability, matte surface finish
- High heat distortion temperature, good low temperature toughness

PROPERTIES	CONDITION	ENGLISH ²	UNITS	SI ²	UNITS	THICKNESS	ASTM
Melt Flow Rate	200°C 5.0 kg	3.0	g/10 min.	3.0	g/10 min.		D1238
Tensile Strength	2.0 in./min.	2,800	psi	19	MPa	0.050 in.	D638
Tensile Modulus	2.0 in./min.	235,000	psi	1,620	MPa	0.050 in.	D638
Tensile Elongation	2.0 in./min.	75	%	75	%	0.050 in.	D638
Flexural Strength	0.1 in./min.	4,600	psi	32	MPa	0.250 in.	D790B
Flexural Modulus	0.1 in./min.	238,000	psi	1,640	MPa	0.250 in.	D790B
Notched Izod Impact	73°F	2.1	ft-lb in.	112	J/m	0.125 in.	D256
Vicat Softening Temp.	Rate B	213	°F	100	°C	0.250 in.	D1525
Deflection Temp.	246 psi	185	°F	85	°C	0.250 in.	D648
Under Load (DTUL)	(1.8 MPa)						
Linear Mold Shrinkage	24 hours	0.004-0.008	in./in.	0.004-0.008	mm/mm		D955
Specific Gravity		1.03					D972
Bulk Density		38-42	lbs./ft. ³				

INJECTION MOLDING - Typical Molding Machine Settings

Zone	SI Conditions	Conditions
Nozzle	213 - 243°C	415 - 470°F
Zone #1	218 - 249°C	425 - 480°F
Zone #2	218 - 249°C	425 - 480°F
Zone #3	199 - 213°C	390 - 415°F
Backpressure	2 - 12 bar	25 - 175 psi

EXTRUSION

Zone	SI Conditions	Conditions
Zone #1	177 - 193°C	350 - 380°F
Zone #2	182 - 204°C	360 - 400°F
Zone #3	188 - 210°C	370 - 410°F
Zone #4	199 - 216°C	390 - 420°F
Zone #5	204 - 221°C	400 - 430°F
Zone #6	204 - 221°C	400 - 430°F
Melt, Pump, Adapter, Pipes,	193 - 232°C	380 - 450°F
Die Changer	199 - 232°C	390 - 450°F
Polish Rolls	66 - 104°C	150 - 220°F
Melt Temp.	193 - 232°C	380 - 450°F
Head Pressure	10 - 21 MPa	1500 - 3000 psi

Product Performance and Suitability Disclaimer

All descriptive information, performance data, and recommendations for the use of Masterpiece Graphix (MGX) products shall be used as a guide only, and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute an MGX company warranty of any kind. All purchasers of MGX products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of MGX is authorized to give any warranty, guarantee, or make any representation in addition or contrary to the above.