



636.349.6401  
 sales@mgxdigital.com  
 www.mgxdigital.com

## MGX-2523

2 mil Bright Silver PET / Permanent / 90# 0-Split  
12" x 18"



Facestock:  
2 mil Silver PET



Adhesive:  
Permanent



Liner:  
90# 0-Split

### DESCRIPTION:

MGX's 2.0 mil bright silver polyester provides aggressive permanent adhesive bonds well to low- and high-surfaces including painted metal, powder-coated paint and plastics. Backed with a lay-flat liner.

### APPLICATIONS:

Brand Labels • Electronics • Appliances • Automotive • Industrial Equipment

	Physical Properties	Value	Test Method
FACESTOCK	Thickness	2 mils (Range +/- 10%)	ASTM D 3652 (Modified for non-tape products)
	Dimensional Stability	No Shrinkage Observed	24 HR dwell time on aluminum panel then 24 HR at 160°F
ADHESIVE	Adhesive Thickness	0.9-1.0 (Range +/-10%)	ASTM D 3652 (Modified for non-tape products)
	Ultimate Peel		ASTM D 903 (Modified for 72 HR Dwell Time)
	ABS	60 oz/in	
	Acrylic	77 oz/in	
	Acrylic Powder Paint	59 oz/in	
	Aluminum	54 oz/in	
	Epoxy Powder Paint	67 oz/in	
	Glass	68 oz/in	
	HDPE 32	32 oz/in	
	Painted Metal	57 oz/in	
	Polycarbonate	58 oz/in	
	Polyester	87 oz/in	
	Polyester Powder Paint	55 oz/in	
	Polypropylene	15 oz/in	
	Polyurethane Powder Paint	72 oz/in	
	Stainless Steel	55 oz/in	
Styrene	54 oz/in		
	Room Temp	30 hours	
	Tack	1030 gm/sq	ASTM D 2979
	Service Temperature Range	-40°F to 302°F	
	Minimum Application Temperature	50°F	
	Storage Stability	Store at 70°F (21°C) and 50% relative humidity	
LINER	Liner Thickness	6.9 +/- 10%	ASTM D 3652 (Modified for non-tape products)

Product Performance and Suitability Disclaimer: All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. MGX shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.