



636.349.6401
 sales@mgxdigital.com
 www.mgxdigital.com

MGX-3590

6 mil White Vinyl / Repositionable / 90# Stripped
13" x 19"



Facestock:
6 mil White Vinyl



Adhesive:
Repositionable



Liner:
90# Stripped

DESCRIPTION:

MGX's 6 mil white flexible vinyl face boasts durability and resistance to oils, chemicals, and select solvents. This versatile substrate is suitable for both indoor and outdoor applications. The 90 lb. heavy-weight, bleached kraft liner is well-suited for roll-to-sheet applications. Additionally, the water-based repositionable adhesive ensures low tack, allowing for clean removal from various surfaces such as paper products, painted walls, floors, and windows.

APPLICATIONS:

Retail Signage • Pop Displays • Interior Decor • Floor Advertising • Window Graphics • Masking • Mouse Pads • Counter Pads

| | Physical Properties | Measure | Value |
|-----------------------|---|---|----------|
| FACESTOCK | Caliper | mils (Range +/- 10% - Normally within 5%) | 6 |
| | Tensile MD | lb/in | 3359 |
| | Tensile CD | lb/in | 3540 |
| | 60 Degree Gloss | | 15 Max |
| | Sheffield Smoothness | | 15 Max |
| | Dyne Level/Surface Energy | Accu-Dyne Pen | 34-38 |
| ADHESIVE | Type | Water-Based, Removable | |
| | Coat Weight | Range 1.25 - 1.45 gms/csi | 1.35 |
| | 180° Peel Data - Stainless - 30 Min Dwell | oz/in | 10.5 |
| | 180° Peel Data - Stainless - 24 Hr Dwell | oz/in | 12.7 |
| | 90° Peel Data - Stainless - 30 Min Dwell | oz/in | 7.5 |
| | 90° Peel Data - Glass - 30 Min Dwell | oz/in | 10.6 |
| | 90° Peel Data - Painted Metal - 30 Min Dwell | oz/in | 15.4 |
| | 90° Peel Data - Semi-Gloss Paint - 30 Min Dwell | oz/in | 7.7 |
| | Polyken Probe | gms | 159 |
| | Application Temperature | °F | 20°F Min |
| Service Temperature | °F | -10°F - 120°F | |
| LINER | Caliper | mils (Range 6.1-7.5) | 6.8 |
| | Tear MD | gms | 100 |
| | Tear CD | gms | 110 |
| | Tensile MD | lb/in | 50 |
| | Tensile CD | lb/in | 35 |
| Regulatory Compliance | | Phthalate-free , CPSIA, CONEG* , EN71, RoHS | |

Product Performance and Suitability Disclaimer: All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. MGX shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.