

MGX-5469 - 26.5" X 38.5" MGX-5171 - 28" X 40"

20 mil Xquisite™ UV Synthetic Paper

## **DESCRIPTION:**

MGX's Xquisite™ is a Polypropylene based Synthetic paper. It's a perfect choice for tear and moisture-resistant applications. The material is chemical resistant, durable and versatile with excellent print quality and color reproduction.

## **APPLICATIONS:**

Plant Tags • Retail Displays • Membership Cards • Food Tags • Maps • Menus • Shelf Talkers

| Physical Properties   | Measure                                     | Actual Value          | Test Method |
|-----------------------|---|-----------------------|-------------|
| Thickness             | mils  | 20                    | Microgauge  |
| Tensile MD            | psi   | 3500                  | ASTM D638   |
| Tensile CD            | psi   | 2000                  | ASTM D638   |
| Elongation MD         | %   | 300                   | ASTM D638   |
| Elongation CD         | %   | 60                    | ASTM D638   |
| Surface Tension (A)   | dyne/cm                                     | 45                    | ASTM D2578  |
| Surface Tension (B)   | dyne/cm                                     | 45                    | ASTM D2578  |
| Roughness 463 EMB (A) | μ"  | 15-35                 | JIS B0601   |
| Roughness 463 EMB (B) | μ"  | 25-60                 | JIS B0601   |
| Gross Value 60% (A)   |   | 2-5                   | ASTM D523   |
| Gross Value 60% (B)   |   | 2-5                   | ASTM D523   |
| Transmittance         | %   | 18↓                   | ASTM D1003  |
| Whiteness             | %   | 78↑                   | ASTM E313   |
| Surface Resistance    |   | <9 x 10 <sup>12</sup> | ADTM D257   |
| Specific Gravity      |   | 1.17±0.03             |             |
| Recycle Code          | 25)<br>PP                                   |                       |             |
| Regulatory Compliancy | RoHS, REACH, CA Prop 65, CPSIA, CSPA, CONEG |                       |             |

Product Performance and Suitability Disclaimer: All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. MGX shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.